



SERIES GT7800 Blinded Project-In Tilt Turn

NFRC U-FACTOR, SHGC / VT, AND CR COMPUTER SIMULATION RESULTS

Standards: NFRC 100-2004, NFRC 200-2004, NFRC 500-2004

ID	U-Factor	SHGC	VT	CR	Fill	Spacer	Exterior Lite	Air Space		Lite # 2	Air Space	Lite # 3	Air Space		Lite # 4
								0.184	Solarban 60				0.223	Clear	
1	0.29	0.26	0.45	50	Argon/Air	Silicone Foam	0.184	Solarban 60	0.625	0.184	Clear	1.731	0.223	Clear	
2	0.29	0.25	0.45	50	Argon/Air	Silicone Foam	0.223	Solarban 60	0.500	0.223	Clear	1.750	0.223	Clear	
3	0.29	0.25	0.45	50	Argon/Air	Silicone Foam	0.223	Solarban 60	0.500	0.266	Clear	1.750	0.223	Clear	
4	0.29	0.25	0.45	50	Argon/Air	Silicone Foam	0.223	Solarban 60	0.500	0.223	Clear	1.750	0.266	Clear	
5	0.29	0.25	0.45	49	Argon/Air	Silicone Foam	0.223	Solarban 60	0.500	0.266	Clear	1.740	0.266	Clear	
6	0.27	0.24	0.42	49	Argon/Air	Silicone Foam	0.223	Solarban 60	0.500	0.223	Clear	1.750	0.222	Pilk LOF	
7	0.30	0.25	0.45	49	Argon/Air	Thermo-plastic	0.223	Solarban 60	0.500	0.223	Clear	1.750	0.223	Clear	
8	0.29	0.25	0.45	50	Argon/Air	Silicone Foam	0.223	Solarban 60	0.563	0.184	Clear	1.740	0.223	Clear	
9	0.29	0.25	0.45	49	Argon/Air	Silicone Foam	0.223	Solarban 60	0.563	0.184	Clear	1.740	0.266	Clear	
10	0.31	0.44	0.47	49	Argon/Air	Silicone Foam	0.223	Clear	0.563	0.186	Pilk LOF	1.740	0.266	Clear	
11	0.31	0.42	0.47	49	Argon/Air	Silicone Foam	0.266	Clear	0.563	0.186	Pilk LOF	1.730	0.266	Clear	
12	0.28	0.39	0.43	48	Argon/Air	Silicone Foam	0.266	Clear	0.563	0.186	Pilk LOF	1.720	0.266	Pilk LOF	
13	0.30	0.25	0.43	49	Argon/Air	Thermo-plastic	0.221	Guard SN 60	0.500	0.221	Clear	1.750	0.221	Clear	
14	0.29	0.25	0.43	50	Argon/Air	Silicone Foam	0.221	Guard SN 60	0.500	0.221	Clear	1.750	0.221	Clear	
15	0.29	0.26	0.43	50	Argon/Air	Silicone Foam	0.223	E272	0.500	0.225	Clear	1.750	0.225	Clear	
16	0.30	0.19	0.41	50	Argon/Air	Stainless Steel	0.187	E366	0.625	0.187	Clear	1.731	0.222	Clear	
17	0.29	0.19	0.40	49	Argon/Air	Stainless Steel	0.225	E366	0.500	0.222	Clear	1.750	0.222	Clear	
18	0.27	0.18	0.37	49	Argon/Air	Stainless Steel	0.225	E366	0.500	0.222	Clear	1.750	0.222	Pilk LOF	
19	0.30	0.24	0.43	49	Argon/Air	Stainless Steel	0.236	Card LowE 270	0.500	0.222	Clear	1.750	0.222	Clear	
20	0.25	0.16	0.28	50	Argon/Argon/Air	Silicone Foam	0.116	E366	0.313	0.116	Clear	0.313	0.116	E366	1.770