

**NFRC 100/200/500 Summary Sheet**  
**Series 0200 Horizontal Slider**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
1	S500/AIR/CLR (6mm/6mm) 1"											
	0.223	0.563	0.223					AIR	0.215(#2)	CL	A1-D	N
	U-Factor 0.58			SHGC (N) 0.46				VT (N) 0.52			CR 34	
2	E366/ARG/E180/ARG/i81 (3mm/3mm/3mm) 1"											
	0.117	0.313	0.118	0.313	0.117			ARG90	0.022(#2) / 0.068(#4) / 0.149(#6)	CL	SS-D	N
	U-Factor 0.42			SHGC (N) 0.18				VT (N) 0.36			CR 36	
3	CLR/ARG/E272/ARG/E272 (3mm/3mm/3mm) 1"											
	0.117	0.313	0.117	0.313	0.117			ARG90	0.042(#3) / 0.042(#5)	CL	SS-D	N
	U-Factor 0.44			SHGC (N) 0.30				VT (N) 0.41			CR 36	
4	CLR/ARG/E272/ARG/i81 (3mm/3mm/3mm) 1"											
	0.117	0.313	0.117	0.313	0.117			ARG90	0.042(#4) / 0.149(#6)	CL	SS-D	N
	U-Factor 0.45			SHGC (N) 0.29				VT (N) 0.42			CR 35	
5	E272/ARG/i89 (5mm/5mm) 1"											
	0.187	0.625	0.187					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.47			SHGC (N) 0.30				VT (N) 0.49			CR 35	
6	E366/ARG/i89 (5mm/5mm) 1"											
	0.187	0.625	0.187					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.21				VT (N) 0.44			CR 35	
7	CLR/AIR/CLR (6mm/6mm) 1"											
	0.225	0.563	0.225					AIR		CL	A1-D	N
	U-Factor 0.66			SHGC (N) 0.54				VT (N) 0.56			CR 33	
	BZ/AIR/CLR (6mm/6mm) 1"											
	0.221	0.563	0.225					AIR		BZ	A1-D	N
	U-Factor 0.66			SHGC (N) 0.38				VT (N) 0.34			CR 33	
	GRY/AIR/CLR (6mm/6mm) 1"											
	0.222	0.563	0.225					AIR		GY	A1-D	N
	U-Factor 0.66			SHGC (N) 0.35				VT (N) 0.28			CR 33	
	GRN/AIR/CLR (6mm/6mm) 1"											
	0.222	0.563	0.225					AIR		GR	A1-D	N
	U-Factor 0.66			SHGC (N) 0.37				VT (N) 0.48			CR 33	

**NFRC 100/200/500 Summary Sheet**  
**Series 0200 Horizontal Slider**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
	BLU/AIR/CLR (6mm/6mm) 1"											
	0.223	0.563	0.225					AIR		BL	A1-D	N
	U-Factor 0.66			SHGC (N) 0.46				VT (N) 0.40			CR 33	
8	E240/ARG/CLR (5mm/5mm) 1"											
	0.187	0.625	0.187					ARG90	0.057(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.19				VT (N) 0.28			CR 36	
9	E270/ARG/CLR (5mm/5mm) 1"											
	0.197	0.625	0.187					ARG90	0.037(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.27				VT (N) 0.49			CR 36	
10	E272/ARG/CLR (5mm/5mm) 1"											
	0.187	0.625	0.187					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.31				VT (N) 0.50			CR 36	
11	E366/ARG/CLR (5mm/5mm) 1"											
	0.187	0.625	0.187					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.21				VT (N) 0.45			CR 36	
12	CMFTE2/AIR/CLR (6mm/6mm) 1"											
	0.222	0.563	0.225					AIR	0.202(#2)	CL	A1-D	N
	U-Factor 0.58			SHGC (N) 0.46				VT (N) 0.52			CR 34	
13	TiAC/AIR/CLR (6mm/6mm) 1"											
	0.221	0.563	0.225					AIR	0.035(#2)	CL	A1-D	N
	U-Factor 0.55			SHGC (N) 0.29				VT (N) 0.41			CR 34	
14	SB60/AIR/CLR (6mm/6mm) 1"											
	0.223	0.563	0.223					AIR	0.035(#2)	CL	A1-D	N
	U-Factor 0.55			SHGC (N) 0.29				VT (N) 0.50			CR 34	
15	SB70/AIR/CLR (6mm/6mm) 1"											
	0.223	0.563	0.223					AIR	0.018(#2)	CL	A1-D	N
	U-Factor 0.55			SHGC (N) 0.21				VT (N) 0.45			CR 34	
16	VE12M/AIR/CLR (6mm/6mm) 1"											
	0.223	0.563	0.223					AIR	0.040(#2)	CL	A1-D	N
	U-Factor 0.55			SHGC (N) 0.29				VT (N) 0.50			CR 34	

**NFRC 100/200/500 Summary Sheet**  
**Series 0200 Horizontal Slider**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
17	CLR/AIR/Lami (6mm/030Lami) 1"											
	0.225	0.500	0.266					AIR		CL	A1-D	N
	U-Factor 0.66			SHGC (N) 0.52				VT (N) 0.56			CR 33	
	BZ/AIR/Lami (6mm/030Lami) 1"											
	0.221	0.500	0.266					AIR		BZ	A1-D	N
	U-Factor 0.66			SHGC (N) 0.37				VT (N) 0.34			CR 33	
	GRY/AIR/Lami (6mm/030Lami) 1"											
	0.222	0.500	0.266					AIR		GY	A1-D	N
	U-Factor 0.66			SHGC (N) 0.35				VT (N) 0.28			CR 33	
	GRN/AIR/Lami (6mm/030Lami) 1"											
	0.222	0.500	0.266					AIR		GR	A1-D	N
	U-Factor 0.66			SHGC (N) 0.37				VT (N) 0.49			CR 33	
	BLU/AIR/Lami (6mm/030Lami) 1"											
	0.223	0.500	0.266					AIR		BL	A1-D	N
	U-Factor 0.66			SHGC (N) 0.44				VT (N) 0.40			CR 33	
18	CLR/AIR/Lami (6mm/090Lami) 1"											
	0.225	0.438	0.326					AIR		CL	A1-D	N
	U-Factor 0.65			SHGC (N) 0.51				VT (N) 0.55			CR 34	
19	E272/ARG/CLR (3mm/3mm) 1"											
	0.117	0.750	0.117					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.31				VT (N) 0.51			CR 36	
20	E272/ARG/CLR (6mm/6mm) 1"											
	0.224	0.563	0.223					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.30				VT (N) 0.49			CR 36	
21	E272/ Arg / Clear (6m/3m) 1.0"											
	0.224	0.625	0.117					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.30				VT (N) 0.50			CR 35	
22	Lami-E272/ Arg / Lami-Clear (6m/6m) 1.0"											
	0.227	0.500	0.250					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.30				VT (N) 0.50			CR 36	

**NFRC 100/200/500 Summary Sheet**  
**Series 0200 Horizontal Slider**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type		
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance			
23	E272/ Arg / Clear (6m/6m) 1.0"													
	0.224	0.500	0.223					ARG90	0.042(#2)	CL	SS-D	N		
	U-Factor		0.50		SHGC (N)			0.30		VT (N)		0.49		CR