

NFRC 100/200/500 Summary Sheet
Updated S0900 Sliding Glass Door

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
1	E272 / ARG90 / CLR (5MM/5MM) - 1-1/8" IG											
	0.187	0.750	0.185					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.44			SHGC (N) 0.32				VT (N) 0.55			CR 50	
2	E272 / ARG90 / i89 (5MM/5MM) - 1-1/8" IG											
	0.187	0.750	0.187					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.39			SHGC (N) 0.32				VT (N) 0.54			CR 43	
3	E366 / ARG90 / CLR (5MM/5MM) - 1-1/8" IG											
	0.187	0.750	0.185					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.22				VT (N) 0.50			CR 50	
4	E366 / ARG90 / i89 (5MM/5MM) - 1-1/8" IG											
	0.187	0.750	0.187					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.22				VT (N) 0.48			CR 43	
5	E270 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.236	0.625	0.224					ARG90	0.037(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.29				VT (N) 0.53			CR 50	
6	E272 / AIR / CLR (6MM/6MM) - 1-1/8" IG											
	0.224	0.625	0.224					AIR	0.042(#2)	CL	SS-D	N
	U-Factor 0.47			SHGC (N) 0.32				VT (N) 0.54			CR 50	
7	E272 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.224	0.625	0.224					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.32				VT (N) 0.54			CR 50	
8	E272 / ARG90 / i89 (6MM/6MM) - 1-1/8" IG											
	0.224	0.625	0.223					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.39			SHGC (N) 0.31				VT (N) 0.53			CR 42	
9	E340 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.224	0.625	0.224					ARG90	0.028(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.15				VT (N) 0.29			CR 50	
10	E366 / AIR / CLR (6MM/6MM) - 1-1/8" IG											
	0.225	0.625	0.224					AIR	0.022(#2)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.22				VT (N) 0.49			CR 50	

**NFRC 100/200/500 Summary Sheet
Updated S0900 Sliding Glass Door**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) <small>Grids (None / <1 / >=1)</small>				Visible Transmittance (VT) <small>Grids (None / <1 / >=1)</small>			Condensation Resistance	
11	E366 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.225	0.625	0.224					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.22				VT (N) 0.49			CR 50	
12	E366 / ARG90 / i89 (6MM/6MM) - 1-1/8" IG											
	0.225	0.625	0.223					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.21				VT (N) 0.48			CR 43	
13	E272 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1-1/8" IG											
	0.224	0.594	0.243					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.32				VT (N) 0.54			CR 50	
14	E366 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1-1/8" IG											
	0.225	0.594	0.243					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.42			SHGC (N) 0.22				VT (N) 0.49			CR 50	
15	SB60 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.223	0.625	0.223					ARG90	0.035(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.31				VT (N) 0.55			CR 49	
16	SB70 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.223	0.625	0.223					ARG90	0.018(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.22				VT (N) 0.50			CR 49	
17	SN68 / AIR / CLR (6MM/6MM) - 1-1/8" IG											
	0.221	0.625	0.221					AIR	0.039(#2)	CL	SS-D	N
	U-Factor 0.47			SHGC (N) 0.30				VT (N) 0.53			CR 47	
18	SN68 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.221	0.625	0.221					ARG90	0.039(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.30				VT (N) 0.53			CR 49	
19	SNX 62/27 / ARG90 / CLR (6MM/6MM) - 1-1/8" IG											
	0.221	0.625	0.221					ARG90	0.020(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.18				VT (N) 0.35			CR 49	
20	SNX 62/27 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1-1/8" IG											
	0.221	0.594	0.243					ARG90	0.020(#2)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.17				VT (N) 0.35			CR 49	