

**NFRC 100/200/500 Summary Sheet
S1400 Series Fixed Window**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
1	RLE6227/ARG90/CLR (6MM/6MM) 1"											
	0.221	0.500	0.221					ARG90	0.024(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.24				VT (N) 0.52			CR 41	
2	RLE7036/ARG90/CLR (6MM/6MM) 1"											
	0.221	0.500	0.221					ARG90	0.036(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.32				VT (N) 0.58			CR 41	
3	VE12M/ARG90/CLR (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.040(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.33				VT (N) 0.61			CR 41	
4	VE148/ARG90/CLR (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.086(#2)	CL	SS-D	N
	U-Factor 0.40			SHGC (N) 0.33				VT (N) 0.41			CR 41	
5	CLR/ARG90/TiPS (6MM/6MM) 1"											
	0.225	0.500	0.224					ARG90	0.063(#3)	CL	SS-D	N
	U-Factor 0.39			SHGC (N) 0.52				VT (N) 0.64			CR 41	
6	CLR/ARG90/CmftE2 (6MM/6MM) 1"											
	0.225	0.500	0.222					ARG90	0.202(#3)	CL	SS-D	N
	U-Factor 0.43			SHGC (N) 0.61				VT (N) 0.63			CR 41	
7	CLR/ARG90/VE185 (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.088(#3)	CL	SS-D	N
	U-Factor 0.40			SHGC (N) 0.51				VT (N) 0.65			CR 41	
8	E272/ARG90/CLR (6MM/6MM) 1"											
	0.224	0.500	0.224					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.35				VT (N) 0.60			CR 42	
9	E270/ARG90/CLR (6MM/6MM) 1"											
	0.236	0.500	0.224					ARG90	0.037(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.32				VT (N) 0.59			CR 42	
10	E366/ARG90/CLR (6MM/6MM) 1"											
	0.225	0.500	0.224					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.24				VT (N) 0.54			CR 42	

**NFRC 100/200/500 Summary Sheet
S1400 Series Fixed Window**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) <small>Grids (None / <1 / >=1)</small>				Visible Transmittance (VT) <small>Grids (None / <1 / >=1)</small>			Condensation Resistance	
11	E240/ARG90/CLR (6MM/6MM) 1"											
	0.224	0.500	0.224					ARG90	0.057(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.22				VT (N) 0.32			CR 42	
12	CLR/ARG90/CLR (6MM/6MM) 1"											
	0.224	0.500	0.224					ARG90		CL	SS-D	N
	U-Factor 0.54			SHGC (N) 0.63				VT (N) 0.69			CR 41	
13	E272/ARG90/i89 (6MM/6MM) 1"											
	0.224	0.500	0.223					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.33			SHGC (N) 0.35				VT (N) 0.59			CR 42	
14	E366/ARG90/i89 (6MM/6MM) 1"											
	0.225	0.500	0.223					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.33			SHGC (N) 0.24				VT (N) 0.53			CR 42	
15	E270/ARG90/i89 (6MM/6MM) 1"											
	0.236	0.500	0.223					ARG90	0.037(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.33			SHGC (N) 0.31				VT (N) 0.57			CR 42	
16	SB60/ARG90/CLR (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.035(#2)	CL	ZF-D	N
	U-Factor 0.38			SHGC (N) 0.34				VT (N) 0.61			CR 42	
17	SB70/ARG90/CLR (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.018(#2)	CL	ZF-D	N
	U-Factor 0.37			SHGC (N) 0.24				VT (N) 0.55			CR 42	
18	CLR/ARG90/S500 (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.215(#3)	CL	ZF-D	N
	U-Factor 0.43			SHGC (N) 0.58				VT (N) 0.63			CR 42	
19	CLR/ARG90/S600 (6MM/6MM) 1"											
	0.223	0.500	0.223					ARG90	0.144(#3)	CL	ZF-D	N
	U-Factor 0.41			SHGC (N) 0.58				VT (N) 0.61			CR 42	
20	RLE6227/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.221	0.440	0.294					ARG90	0.024(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.24				VT (N) 0.52			CR 41	

**NFRC 100/200/500 Summary Sheet
S1400 Series Fixed Window**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) <small>Grids (None / <1 / >=1)</small>				Visible Transmittance (VT) <small>Grids (None / <1 / >=1)</small>			Condensation Resistance	
21	RLE7036/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.221	0.440	0.294					ARG90	0.036(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.31				VT (N) 0.58			CR 41	
22	VE12M/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.223	0.440	0.318					ARG90	0.040(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.33				VT (N) 0.61			CR 41	
23	VE148/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.223	0.440	0.318					ARG90	0.086(#2)	CL	SS-D	N
	U-Factor 0.39			SHGC (N) 0.33				VT (N) 0.41			CR 41	
24	E272/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.224	0.440	0.304					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.35				VT (N) 0.59			CR 42	
25	E270/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.236	0.440	0.304					ARG90	0.037(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.31				VT (N) 0.58			CR 42	
26	E366/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.225	0.440	0.304					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.24				VT (N) 0.53			CR 42	
27	E240/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.224	0.440	0.304					ARG90	0.057(#2)	CL	SS-D	N
	U-Factor 0.38			SHGC (N) 0.22				VT (N) 0.32			CR 42	
28	SB60/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.223	0.440	0.318					ARG90	0.035(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.34				VT (N) 0.61			CR 42	
29	SB70/ARG90/CLR-LAMI (6MM/3MM 060PVB 3MM) 1"											
	0.223	0.440	0.318					ARG90	0.018(#2)	CL	SS-D	N
	U-Factor 0.37			SHGC (N) 0.24				VT (N) 0.55			CR 42	