

**NFRC 100/200/500 Summary Sheet  
SR6700 Casement**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
1	E272 / ARG90 / CLR (5MM/5MM) - 1" IG											
	0.187	0.625	0.185					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.31				VT (N) 0.52			CR 34	
2	E272 / ARG90 / i89 (5MM/5MM) - 1" IG											
	0.187	0.625	0.187					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.31				VT (N) 0.50			CR 34	
3	E366 / ARG90 / CLR (5MM/5MM) - 1" IG											
	0.187	0.625	0.185					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.22				VT (N) 0.47			CR 34	
4	E366 / ARG90 / i89 (5MM/5MM) - 1" IG											
	0.187	0.625	0.187					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.21				VT (N) 0.45			CR 34	
5	E270 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.236	0.500	0.224					ARG90	0.037(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.28				VT (N) 0.50			CR 34	
6	E272 / AIR / CLR (6MM/6MM) - 1" IG											
	0.224	0.500	0.224					AIR	0.042(#2)	CL	SS-D	N
	U-Factor 0.53			SHGC (N) 0.31				VT (N) 0.51			CR 34	
7	E272 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.224	0.500	0.224					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.31				VT (N) 0.51			CR 34	
8	E272 / ARG90 / i89 (6MM/6MM) - 1" IG											
	0.224	0.500	0.223					ARG90	0.042(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.30				VT (N) 0.50			CR 34	
9	E340 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.224	0.500	0.224					ARG90	0.028(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.15				VT (N) 0.28			CR 34	
10	E366 / AIR / CLR (6MM/6MM) - 1" IG											
	0.225	0.500	0.224					AIR	0.022(#2)	CL	SS-D	N
	U-Factor 0.53			SHGC (N) 0.22				VT (N) 0.46			CR 34	

**NFRC 100/200/500 Summary Sheet  
SR6700 Casement**

ID	Pane Thickness 1	Gap Width 1	Pane Thickness 2	Gap Width 2	Pane Thickness 3	Gap Width 3	Pane Thickness 4	Gap Fill	Low-e (Surface#)	Tint	Spacer	Grid Type
	U-Factor			Solar Heat Gain Coefficient (SHGC) Grids (None / <1 / >=1)				Visible Transmittance (VT) Grids (None / <1 / >=1)			Condensation Resistance	
11	E366 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.225	0.500	0.224					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.22				VT (N) 0.46			CR 34	
12	E366 / ARG90 / i89 (6MM/6MM) - 1" IG											
	0.225	0.500	0.223					ARG90	0.022(#2) / 0.149(#4)	CL	SS-D	N
	U-Factor 0.46			SHGC (N) 0.21				VT (N) 0.45			CR 34	
13	E272 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1" IG											
	0.224	0.469	0.243					ARG90	0.042(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.31				VT (N) 0.51			CR 33	
14	E366 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1" IG											
	0.225	0.469	0.243					ARG90	0.022(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.22				VT (N) 0.46			CR 33	
15	SB60 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.223	0.500	0.223					ARG90	0.035(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.30				VT (N) 0.51			CR 34	
16	SB70 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.223	0.500	0.223					ARG90	0.018(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.22				VT (N) 0.47			CR 34	
17	SN68 / AIR / CLR (6MM/6MM) - 1" IG											
	0.221	0.500	0.221					AIR	0.039(#2)	CL	SS-D	N
	U-Factor 0.54			SHGC (N) 0.30				VT (N) 0.50			CR 33	
18	SN68 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.221	0.500	0.221					ARG90	0.039(#2)	CL	SS-D	N
	U-Factor 0.51			SHGC (N) 0.29				VT (N) 0.50			CR 34	
19	SNX 62/27 / ARG90 / CLR (6MM/6MM) - 1" IG											
	0.221	0.500	0.221					ARG90	0.020(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.18				VT (N) 0.33			CR 34	
20	SNX 62/27 / ARG90 / CL-LAMI (6MM/2.7 030 PVB 2.7) - 1" IG											
	0.221	0.469	0.243					ARG90	0.020(#2)	CL	SS-D	N
	U-Factor 0.50			SHGC (N) 0.18				VT (N) 0.32			CR 33	